

**EFFECTS OF IMPACT VELOCITY AND STRESS  
CONCENTRATORS IN TITANIUM ON FAILURE  
BY ADIABATIC SHEARING**

Third Interim Report  
( March 25/99 - June 24/99 )

Principal Investigator: J.R.KLEPACZKO

**UNITED STATES ARMY EUROPEAN RESEARCH OFFICE  
LONDON , UK**

CONTRACT N°: N68171-98-M-5829  
R&D no: 8377-AN-01 .

Contractor:

Laboratory of Physics and Mechanics of Materials  
ISGMP , UMR - CNRS 7554  
METZ UNIVERSITY  
F-57045 Metz, France

**DISTRIBUTION STATEMENT A**  
**Approved for Public Release**  
**Distribution Unlimited**

Approved for public release  
Distribution unlimited

**DTIC QUALITY INSPECTED 4**

**19991004 228**

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204 Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave Blank)	2. REPORT DATE August 19 / 1999	3. REPORT TYPE AND DATES COVERED INTERIM, March 25 / 1999 - June 24 / 1999		
4. TITLE AND SUBTITLE EFFECTS OF IMPACT VELOCITY AND STRESS CONCENTRATORS IN TITANIUM ALLOYS ON FAILURE BY ADIABATIC SHEARING			5. FUNDING NUMBERS N68171-98-M-5829	
6. AUTHOR(S) J.R. KLEPACZKO				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) METZ UNIVERSITY - ISGMP LAB. OF PHYSICS AND MECHANICS OF MATERIALS ILE DU SAULCY, F-57045 METZ cedex 1, FRANCE			8. PERFORMING ORGANIZATION REPORT NUMBER N/A	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) USA RDSG-UK, AERONAUTICS AND MECHANICS BRANCH Dr. Sam SAMPATH 223 OLD MARYLEBONE RD. LONDON NW1-5TH, U.K.			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT DISTRIBUTION UNLIMITED			12b. DISTRIBUTION CODE N/A	
13. ABSTRACT (Maximum 200 words)  This Interim Report covers the contract period from March 25/1999 to June 24/1999 (the third period of three months). During this period the first series of the MDS (Modified Double Shear) specimens have been machined and the main part of experiments has been performed. The experiments were limited in this series to relatively low strain rates in shear, from $10^{-3}$ 1/s to $5 \times 10^2$ 1/s. A fast hydraulic testing machine together with a special device to fix the MDS specimen was used. The oscillograms have been analyzed and variety of test data obtained for the Ti-6Al-4V alloy. It has been found that this alloy is very rate sensitive and the flow stress in this range of strain rates is proportional to the logarithm of strain rate. New series of experiments was prepared to test this alloy in shear at high and very high strain rates, up to $\sim 10^5$ 1/s. The measuring system for the impact experiments on MDS specimens was put into operation.				
14. SUBJECTS ITEMS ADIABATIC SHEAR BANDS, TITANIUM ALLOY Ti-6Al-4V, STRESS CONCENTRATORS IN IMPACT, DYNAMIC PLASTICITY			15. NUMBER OF PAGES 01	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT	

NSN 7540-01-280-5500

Standard Form 298 (Rev.2-89)  
Prescribed by ANSI Std. Z39-18  
298-102

## EXTENDED ABSTRACT

During the third period (three months from March 25/98 to June 24/99) of the Contract the experimental program was started. The first series of the MDS (Modified Double Shear) specimens of Ti-6Al-4V alloy have been machined and the first series of experiments has been performed. The material (Ti-6Al-4V) was delivered by the ARL - Aberdeen, MD. The experiments were limited in this series of tests to relatively low strain rates in shear, from  $10^{-3}$  1/s to  $5 \times 10^2$  1/s. A fast hydraulic universal testing machine together with a special device to fix and load the MDS specimen were used. The device has its own gage system to measure force and displacement as a function of time, [1]. It was found that this titanium alloy is very rate sensitive in this range of strain rates and the flow stress is proportional to the logarithm of strain rate. This is important because a variety of data must be collected, including effects of strain hardening, and also effects of strain rate and temperature, in order to properly construct the final constitutive relations. The literature data which were analyzed previously using many sources have been compared with the own data (double shear with MDS specimens). In this way the trends were found how the strain hardening curves for Ti-6Al-4V change as a function of strain rate and temperature. A wide range of strain rates, from quasi-static to about  $10^3$  1/s, was covered in this analysis. The experimental results have been used to verify the constitutive relation developed at LPMM. This relation which takes into account the strain hardening, strain rate and temperature has been updated for Ti-6Al-4V alloy, and all material constants for this alloy have been found.

The LPMM has developed under previous contracts partially granted by the European Research Office of the US Army, a unique experimental technique which permits for shear testing of materials within wide range of strain rates, typically from  $10^{-4}$  1/s to  $10^5$  1/s, that is nine decimal orders in strain rate [1]. This technique is used to study titanium alloy Ti-6Al-4V up to strain rate  $10^5$  1/s, including formation of ASB's (Adiabatic Shear Bands).

Since the experimental technique with the MDS specimens loaded by direct impact is quite complicated, the setup tuned up and the preliminary series of experiments was performed (strain rate in shear up to  $10^5$  1/s). The oscillograms are under analysis. Those experiments, quasi-static and direct impact on MDS specimens will serve to verify the constitutive relation at very high strain rates as well as the CIV in shear (Critical Impact Velocity), [2].

Cont.

## Refernces

- [1] J.R.Klepaczko, An Experimental Technique for Shear Testing at High and Very High Strain Rates, the Case of Mild Steel, *Int. J. Impact Engng.*, **15** (1994), 25.
- [2] J.R.klepaczko and M.Klosak, Numerical Study of the Critical Impact Velocity in Shear, *Eur. J. Mech. A/Solids*, **18** (1999), 93.

Research reported in this document has been made possible through the support and sponsorship of the US Government through its European Research Office of the US Army. This Interim Report is intended only for the internal management use of the Contractor and the US Government.